



Mid-Western States

ProMar[®]

**INTERIOR LATEX
 MOISTURE VAPOR BARRIER PRIMER/FINISH
 B72WF210**

CHARACTERISTICS

ProMar Interior Latex Moisture Vapor Barrier Primer/Finish is a coating designed to reduce the loss of moisture through walls and ceilings. This product is designed for one coat application in manufactured housing facilities. Upon priming drywall or field installation of the home, this product can be topcoated with any Sherwin-Williams' interior latex or alkyd product.

Color: White
Coverage:
 Recommended: 350 sq ft/gal
 @ 4.5 mils wet, 1.5 mils dry
Drying Time @ 77°F 50% RH
 (temperature and humidity dependant)
 To touch: 30 minutes
 To topcoat: 1 hour
Finish: 0-10 @ 85°
Flash Point: 201°F, PMCC
Perm Rating: less than 1.0 perms
 ASTM E96-A
Solvent/Reducer: Water
Tinting with Blend-A-Color:

Base	oz/gal	Strength
White	0-4	100%

Vehicle Type: Styrene Butadiene
VOC: 80 gr/L; 0.69 lb/gal
Volume Solids: 30 ± 2%
Weight Solids: 43 ± 2%
Weight per Gallon: 10.2 lb

APPLICATION

Do not thin. Reduction will adversely affect the perm rating.
 Apply at temperatures above 50°F.

Brush - Use nylon/polyester brush
Roller - Use 3/8" - 3/4" nap cover
Spray - Airless
Pressure 2000 psi
Tip017"-.019"

SPECIFICATIONS

Drywall
System 1:
 1-2 cts. ProMar Interior Latex Moisture Vapor Barrier Primer/Finish
System 2:
 1 ct. ProMar Interior Latex Moisture Vapor Barrier Primer/Finish
 2 cts. Sherwin-Williams interior, Latex or Alkyd, Architectural Topcoat

CLEANUP INFORMATION

Clean spills and spatters immediately with soap and warm water. Clean hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with mineral spirits to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using mineral spirits.

LABEL ANALYSIS

B72WF210

Pigment by Weight	27%
Titanium Dioxide	10%
Silica/Silicates	10%
Calcium Carbonate	7%
Vehicle by Weight	73%
Styrene Butadiene Resin	12%
Vinyl Acrylic Resin	2%
Water	55%
Additives	4%
Total	100%

SURFACE PREPARATION

Remove all surface contamination by washing with ProClean All Surface Cleaner or other appropriate cleaner, rinse thoroughly and allow to dry. Existing peeled or checked paint should be scraped and sanded to a sound surface. Glossy surfaces should be sanded dull. Stains from water, smoke, ink, pencil, grease, etc. should be sealed with PrepRite ProBlock Primer Sealer.

Drywall

Fill cracks and nail holes with patching paste/spackle and sand smooth. Joint compounds must be cured and sanded smooth. Remove all sanding dust.

CAUTIONS

Protect from freezing.
 Non-photochemically reactive.

CAUTION contains CRYSTALLINE SILICA. Use only with adequate ventilation. To avoid overexposure, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches, or dizziness, increase fresh air, or wear respiratory protection (NIOSH/MSHA TC23C or equivalent) or leave the area. Adequate ventilation required when sanding or abrading the dried film. If adequate ventilation cannot be provided wear an approved particulate respirator (NIOSH/MSHA TC21C or equivalent). Follow respirator manufacturer's directions for respirator use. Avoid contact with eyes and skin. Wash hands after using. Keep container closed when not in use. Do not transfer contents to other containers for storage. **FIRST AID:** In case of eye contact, flush thoroughly with large amounts of water. Get medical attention if irritation persists. If swallowed, get medical attention immediately. **DELAYED EFFECTS FROM LONG TERM OVEREXPOSURE.** Abrading or sanding of the dry film may release crystalline silica which has been shown to cause lung damage and cancer under long term exposure. **WARNING:** This product contains chemicals known to the State of California to cause cancer. **DO NOT TAKE INTERNALLY. KEEP OUT OF THE REACH OF CHILDREN.**

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Sheet.