

Icynene ProSeal™ Best Practices

In order to properly process Icynene ProSeal™ and to maximize yield, please adhere to the following guidelines:

Storage:

- Once received, ProSeal™ drums should be stored at 60°F to 85°F.
- ProSeal™ drums should be stored out of direct sunlight and out of cold temperatures.
- Do not store material on rigs other than what is required for current application needs, as materials left inside of rigs can easily exceed these recommended storage temperatures.
- ProSeal™ B-side resin has a 12 month shelf life if stored as stated.
- Follow FIFO (First-In-First-Out) stock rotation.

Mixing:

- **Note:** Icynene ProSeal™ does not require any mixing prior to or during application.
- If changing to Icynene ProSeal™ from another product follow the changeover procedure below.

Heating:

- Drum temperatures for processing Icynene ProSeal™ (B-side Resin and A-side Iso) need to be between 60°F and 85°F.
- **In cooler weather the Icynene ProSeal™ drums should be kept at the stated storage temperature range so that pre-heating is not necessary.**
- Drum band heaters or electrically heated drum blankets can be used to warm and maintain the drum temperatures between 60°F and 85°F.
- Do not exceed 85°F as the blowing agent will start to come out of the resin blend which may lead to frothing, poor quality foam, and a possible pressure build up in the drum.
- **Note:** Do not circulate the Icynene ProSeal™ B-side resin to warm the drum.

Best Practices & Guide



Processing Temperature and Pressure:

- In standard ambient conditions the following are recommended for processing ProSeal™:

Drum Temperatures: 60°F to 85°F

All heaters for ProSeal LE™ 115°F to 125°F

Mix Chamber: AR5252 (02 Round)

Pressure: 1200 psi (dynamic)

Spray Distance: 18" to 24"

- In cooler weather, increase the A, B and Hose heats gradually.
- In warmer weather, decrease the A, B and Hose heats gradually.
- To maximize yield Icynene recommends using an AR5252 (02 round) at 1200 psi dynamic pressure. If it is necessary to use another sized chamber, use the following guidelines:

<u>Mix Chamber Size</u>	<u>Pressure (dynamic)</u>	<u>Distance</u>
00 (2929)	700-900 psi	14" - 18"
01 (4242)	900-1100 psi	18" - 24"
02 (5252)	1000-1300 psi	18" - 24"
03 (6060)	1200-1500 psi	18" - 24"

Please be aware that altering recommended settings may cause poor foam quality and a substantial reduction in yield.

Environmental Issues:

- Icynene ProSeal™ may be sprayed at ambient / substrate temperatures between 23°F to 122°F
- Use wind screens if spraying where the wind speed is over 10mph.
- Wet, saturated substrates will cause bubbling in the foam and loss of adhesion.
- Substrates must be clean, dry and free of contaminants such as grease, oil and solvents.

Spray Technique:

- Maintain the proper distance as recommended above.
- Always spray with the spray gun at a 90 degree angle to the substrate.
- For wall cavities the best technique is to "picture frame" the studs and then to vertically fill in the middle in 24" to 36" sections while overlapping by 50 percent.
- For flat concrete or metal substrates maintain a gun angle of 90 degrees and a spray distance of around 18" to 24" (depending on chamber size and psi) with an overlap of around 50 percent.
- Build thickness by spraying on to the expanding material (known as the "cream").

Houston | Corporate Office

15402 Vantage Parkway East, Suite 322

Houston, TX 77032

Phone: (281) 219-4100 Fax: (281) 219-4102

icynene-lapolla.com

Mississauga

6747 Campobello Road, Mississauga

Ontario, Canada L5N 2L7

Phone: 1-800-758-7325

Best Practices & Guide



- “Flashing” is recommended for best adhesion to cold substrates.
- Spray a minimum of ½” per pass so as to not affect the foam’s adhesion.
- **ICYNENE ProSeal™ can be sprayed up to 4 inches for first pass only, the 2 inches maximum for additional passes.**
For thicknesses greater than 4 inches, the above procedure can be repeated after 30 minutes or until the surface temperature has returned to ambient.
- **Spraying too thick in one pass or spraying multiple passes without waiting for the foam to cool can cause the foam to scorch or even to catch fire due to excessive heat build-up within the foam.**

Changeover:

- **If you are changing in to ProSeal™ from another product you must not allow the other product to contaminate the ProSeal™ resin drum.**
 - Make sure the drum pump and pump housing are completely free of the previous resin.
 - Allow some air in to the drum pump.
 - Put the drum pump in to the drum of ProSeal™ resin.
 - If you have a re-circulation/pressure-relief line, pump the contents to the previous drum or into a waste container with the transfer pumps.
 - Connect the re-circulation/pressure relief line to the ProSeal™ drum lid.
 - Remove the gun from the hose manifold and pump the hose contents in to the previous drum until you see a color change or until you reach the air pocket in the line.
 - Keep the hose heat on at 125°F during changeover.
 - There will be some mixture of the two resins in the line which you can run in to a container for disposal or spray out as foam for disposal.
 - Spray a test bun and watch for good foam with no collapse.
- Make sure recommended settings are followed before installing ProSeal™ as outlined above.

Before spraying Icynene ProSeal™ for the first time you should contact Icynene-Lapolla Technical Services for installation guidance.

REVISION DATE: 7/22/2019

Houston | Corporate Office
15402 Vantage Parkway East, Suite 322
Houston, TX 77032
Phone: (281) 219-4100 Fax: (281) 219-4102
icynene-lapolla.com

Mississauga
6747 Campobello Road, Mississauga
Ontario, Canada L5N 2L7
Phone: 1-800-758-7325